

TEST REPORT

NUMBER : DP11744
DATE : July 8, 2008

TESTS CONDUCTED :

1. MIGRATION TEST FOR PLASTIC FOOD CONTACTING MATERIALS/ARTICLES:
(AS PER UK S.I NO. 1376 (1998), S.I. NO. 3162 (2000) AND S.I. NO. 2364 (2002) PLASTIC MATERIALS AND ARTICLES IN CONTACT WITH FOOD REGULATIONS)

[A]

I. CONDITION OF CONTACT IN ACTUAL USE:

TEMPERATURE: $\leq 40^{\circ}\text{C}$ TIME: ≤ 24 HOURS

II. TEST CONDITION:

<u>FOOD SIMULANT</u>	<u>TIME</u>	<u>TEMPERATURE</u>
3% (W/V) ACETIC ACID IN AQUEOUS SOLUTION	24 HOURS	40°C

III. TEST RESULTS:

<u>FOOD SIMULANT</u>	<u>RESULT (mg/dm²)</u>	<u>LIMIT</u>
3% (W/V) ACETIC ACID IN AQUEOUS SOLUTION	<1	10

REMARK: < = LESS THAN